

S-Print®



**Compact, flexible
sand 3D printer delivering
accurate and complex designs
straight from CAD files**

The S-Print® combines a compact structure with the ability to process all ExOne binder systems to support a versatile range of applications. An ideal solution for rapid product development and flexible short run production, the S-Print can process various media to create molds and cores for a wide range of casting materials without the cost and lead time of tooling.

TECHNICAL DATA

Job box (L × W × H)	800 × 500 × 400 mm (31.5 × 19.7 × 15.8 in)	External dimensions (L × W × H)	3.3 × 2.5 × 2.9 m (10.8 × 11.5 × 9.5 ft)
Build volume	160 l (5.6 ft ³)	System weight	3,500 kg (7,716 lbs)
Build rate*	Up to 40 l/h	Binder systems	Furan, CHP, HHP, Inorganic
Layer height**	0.2 to 0.5 mm (200 to 500 μm)	Print media	Natural and synthetic sands
Dimensional accuracy	+/- 0.5 mm (500 μm)	Additives	Iron Oxide, Magnesium Inhibitor
Loss on ignition (LOI)***	1.0 - 2.1 %	Electrical requirements	400 V AC (±10%), 3ph/PE/N
Reclaim**	30%	Exhaust air	300 - 600 m ³ /h

* Depending on layer height. ** Depending on material. *** Depending on part size and geometry (0.1% of part size)

SYSTEM BENEFITS

- Flexible system supports an extremely versatile range of metalcasting and tooling applications
- Able to process all ExOne binder systems (Furan, CHP, HHP, Inorganic) and casting media including silica to ceramic sand
- Perfect choice for prototypes and small series
- Precise production of complex geometries and consolidated cores
- Compact footprint for easy integration

www.exone.com

ExOne disclaims all warranties and liabilities for the content hereof and makes no representations as to its accuracy or fitness for use for any purpose. Any tradenames, trademarks, or service marks of others appearing herein are used strictly nominatively and are not to be construed as implying any affiliation connection, association, sponsorship, or approval of the owners thereof for ExOne, its products, or the content hereof. Specifications are subject to change without notice. Some data may be dependent on size and characteristics of powder being processed.

© Desktop Metal 2022, X1_Datasheet_S-Print_EN_2022-04

